



H93 Cement Board

H grades are cement boards designed to provide outstanding service in high temperature applications.

**Product
Description**

H93 has been specially developed to provide outstanding service in demanding thermal applications, where a quality, high strength, machineable engineering board is required. H93 is used in demanding heat and electrical insulation applications in induction furnaces, billet heater boxes, oven cladding, cathode support pads, furnaces and smelters. It is the industry standard for high temperature insulation boards and structural insulation boards.

**Product
Advantages**

- High Strength
- High Machinability
- Excellent Thermal Resistance
- Excellent Electrical Resistance
- High Quality Products
- High Toughness
- Dimensionally Stable
- Non Combustible
- Chemically Inert
- Mechanical Strength at Temperature
- Resistant to most molten metals

Technical Data

Property	Unit	Value
Density	g / cm3	1.8
Compressive strength	MPa @ ambient	107
Flexural strength	MPa @ ambient	30
Impact strength	KJ/mm @ Ambient	6.5
Linear shrinkage	% 24 hrs @ 350°C	0.4
Water absorption	% 24 hrs @ ambient	8 max
Electric strength	KV/mm @ 90°C	2.1
Surface Breakdown	KV/mm @ 90°C	14
Maximum continuous operating temperature	°C	700

Approved Applications

- Induction furnaces
- Billet heater boxes
- Oven cladding
- Cathode support pads
- Furnaces and smelters

Sizes

Standard sheet sizes are 1245 x 940 mm, with thickness between 6 and 75 mm. Alternatively, machined components are available on request to customer drawings.

Maintenance

Periodic visual inspection is recommended.

Storage

- To be stored in a dry location
- Take care not to exceed safe working loads and heights for storage shelves and racks



H93 Cement Board

ARCLEX

FEROFORM

FIREFLY

NITRASIL

REFEL

**REFRACTORY
PRODUCTS**

REFRAVER

Tenmat Ltd
Ashburton Rd West, Manchester
M17 1TD United Kingdom

+44 161 872 2181
info@tenmat.com

tenmat.com



Advanced materials.
tenmat.com

Tenmat warrants the materials it produces will conform to Tenmat specifications and approved drawings where applicable. It is entirely the customer's responsibility to make the final product choice and satisfy themselves of the suitability of the product for the intended application, carrying out testing where required. For construction projects, all products which the customer is intending to use on a particular project must be approved in writing by the customer's building designer, system designer or design control professional, to ensure compliance with the latest regulations.

The information contained in Tenmat data sheets is presented in good faith. The values are "typical only" and are based on test results generally in accordance with BS2782, ASTM, a variety of other main test bodies along with Tenmat internal test methods. These values should not be relied upon for specification purposes or the primary selection of materials. As the data sheet values are typical only, Tenmat does not warrant the conformity of its materials to these properties or the suitability of its materials for any particular purpose. It is the responsibility of the customer to do the necessary testing and satisfy themselves the product is suitable for the intended application.