

Advanced materials. tenmat.com

RAILKO-NF22

Brake Linkage Bushes

RAILKO NF22 Brake Linkage Bushes are used within freight and passenger vehicles in the articulation points of the braking system.

Wear Components

| Product Description | RAILKO NF22 reinforced composite bushes are proven to lower noise by up to 13dB (A), compared with steel bushes. RAILKO NF22 reinforced composite bushes provide protection to pins, shafts and housings against costly wear. It is important to ensure the material has a low water swell and thermal expansion, thus avoiding seizing issues on the pin shaft, which can affect the wagon braking mechanism. The RAILKO NF22 Brake Linkage Bushes have a very low water swell and thermal expansion, which enables tighter running clearances and longer bearing life. | |
|-----------------------|---|--|
| Product Advantages | Significantly lower noise than steel Prevents shaft seizures - Maintenance free solution High resistance to abrasive conditions - Longer component life time Less downtime Ease of installation | |
| Approved Applications | For use as Brake Linkage Bushes in the braking system in passenger/freight rail. | |
| Storage | To be stored in a dry location Take care not to exceed safe working loads and heights for storage shelves and racks | |



Physical Properties

| Property | Units | NF |
|--|-----------|-----------|
| Density | g/cm³ | 1.64 |
| Flexural Strength | MPa | 44 |
| Flexural Modulus | GPa | 5.7 |
| Compressive Strength | MPa | 190 |
| Tensile Strength | MPa | 27 |
| Charpy Impact Notched | kJ/m² | 30 |
| Shear Strength | MPa | 40 |
| Compressive Yield @ 68.9 Mpa | % | 2.0 |
| Shore D Hardness | | 90 |
| Swell in Water (24 hours) | % | |
| 20 °C | | 0.2 |
| 80 °C | | 0.5 |
| Coefficient of Thermal Expansion | x 10-6/°C | |
| Parallel | | 43 |
| Perpendicular | | 43 |
| Coefficient of Friction (Unlubricated) | | 0.34-0.42 |
| Maximum Operating Temperature | °C | |
| Continuous | | 120 |
| Intermittent | | 140 |
| Normal Working Pressure | MPa | 55 |





RAILKO NF22

Tenmat Ltd Ashburton Rd West, Manchester M17 1TD United Kingdom

+44 161 872 2181 info@tenmat.com

tenmat.com



Advanced materials. tenmat.com

Tenmat warrants the materials it produces will conform to Tenmat specifications and approved drawings where applicable. It is entirely the customer's responsibility to make the final product choice and satisfy themselves of the suitability of the product for the intended application, carrying out testing where required. For construction projects, all products which the customer is intending to use on a particular project must be approved in writing by the customer's building designer, system designer or design control professional, to ensure compliance with the latest regulations.

The information contained in Tenmat data sheets is presented in good faith. The values are "typical only" and are based on test results generally in accordance with BS2782, ASTM, a variety of other main test bodies along with Tenmat internal test methods. These values should not be relied upon for specification purposes or the primary selection of materials. As the data sheet values are typical only, Tenmat does not warrant the conformity of its materials to these properties or the suitability of its materials for any particular purpose. It is the responsibility of the customer to do the necessary testing and satisfy themselves the product is suitable for the intended application.